

The following Listing of Claims will replace all prior versions, and listings, of claims in the present application:

Listing of Claims:

1-20 (Canceled)

21. (Currently amended) A multi-layer dielectric layer over a substrate for use in dual-damascene applications, comprising:

a barrier layer disposed over the substrate[[]], and

an inter-metal dielectric structure, the inter-metal dielectric structure consisting of:

_____ i) _____ an inorganic dielectric layer disposed over the barrier layer, the inorganic dielectric layer having a dielectric constant of about 4; and

_____ ii) _____ a low dielectric constant layer disposed directly over and in direct contact with the inorganic dielectric layer;

wherein the low dielectric constant layer is configured to receive metallization line trenches to define a metallization line layer and the inorganic dielectric layer is configured to receive vias during a dual-damascene process.

22. (Original) A multi-layer dielectric layer over a substrate for use in dual-damascene applications as recited in claim 21, wherein the barrier layer is one of a silicon nitride layer and a silicon carbide layer.

23. (Original) A multi-layer dielectric layer over a substrate for use in dual-damascene applications as recited in claim 22, wherein the inorganic dielectric layer is one of an un-doped TEOS oxide and a fluorine doped oxide.

24. (Original) A multi-layer dielectric layer over a substrate for use in dual-damascene applications as recited in claim 23, wherein the low dielectric constant layer is a carbon doped oxide.

25. (Canceled)

26. (Previously Presented) A multi-layer dielectric layer over a substrate for use in dual-damascene applications as recited in claim 24, wherein the inorganic dielectric layer has different material properties than the low dielectric constant layer.

27. (Previously Presented) A multi-layer dielectric layer over a substrate for use in dual-damascene applications as recited in claim 26, wherein a thickness of the inorganic dielectric layer is about 4500 Angstroms.

28. (Previously Presented) A multi-layer dielectric layer over a substrate for use in dual-damascene applications as recited in claim 27, wherein a thickness of the low dielectric constant layer is about 5000 Angstroms.

29. (Previously Presented) A multi-layer dielectric layer over a substrate for use in dual-damascene applications as recited in claim 26, wherein a thickness of the low dielectric constant layer is greater than a thickness of the inorganic dielectric layer.

30. (Previously Presented) A multi-layer dielectric layer over a substrate for use in dual-damascene applications as recited in claim 29, wherein the thickness of the inorganic dielectric layer is about at least 1,000 Angstroms, and the thickness of the low dielectric constant layer and the inorganic dielectric layer is about 10,000 Angstroms.

31. (Currently amended) A multi-layer inter-metal dielectric semiconductor structure, comprising:

a barrier layer disposed over a base dielectric layer[[]], and

the multi-layer inter-metal dielectric semiconductor structure consisting of:

i.) an inorganic dielectric layer of an un-doped TEOS oxide disposed over the barrier layer; and

ii) a low dielectric constant layer of a carbon doped oxide disposed directly over and in direct contact with the inorganic dielectric layer;

wherein the low dielectric constant layer is configured to receive metallization line trenches to define a metallization line layer and the inorganic dielectric layer is configured to receive vias during a dual-damascene process.

32. (Previously Presented) A multi-layer inter-metal dielectric semiconductor structure as recited in claim 31, wherein a thickness of the inorganic dielectric layer of an un-doped TEOS oxide is about 4500 Angstroms.

33. (Previously Presented) A multi-layer inter-metal dielectric semiconductor structure as recited in claim 32, wherein a thickness of the low dielectric constant layer of a carbon doped oxide is about 5000 Angstroms.

34. (Previously Presented) A multi-layer inter-metal dielectric semiconductor structure as recited in claim 31, wherein a thickness of the low dielectric constant layer of a carbon doped oxide is greater than a thickness of the inorganic dielectric layer of an un-doped TEOS oxide.

35. (Previously Presented) A multi-layer inter-metal dielectric semiconductor structure as recited in claim 34, wherein the thickness of the inorganic dielectric layer of an un-doped TEOS oxide is about at least 1,000 Angstroms, and the thickness of the low dielectric constant layer of a carbon doped oxide and the inorganic dielectric layer of an un-doped TEOS oxide is about 10,000 Angstroms.

36. (Currently amended) A dielectric structure for dual-damascene applications, comprising:

a barrier disposed over a base dielectric; and

an inter-metal dielectric structure, the inter-metal dielectric structure consisting of:

_____ i) _____ an inorganic dielectric layer of a fluorine doped oxide disposed over the barrier; and

_____ ii) _____ a low dielectric constant layer of a carbon doped oxide disposed directly over and in direct contact with the inorganic dielectric layer;

wherein the low dielectric constant layer is configured to receive metallization line trenches to define a metallization line layer and the inorganic dielectric layer is configured to receive vias during a dual-damascene process.

37. (Previously Presented) A dielectric structure for dual-damascene applications as recited in claim 36, wherein a thickness of the inorganic dielectric layer of a fluorine doped oxide is about 4500 Angstroms.

38. (Previously Presented) A dielectric structure for dual-damascene applications as recited in claim 37, wherein a thickness of the low dielectric constant layer of a carbon doped oxide is about 5000 Angstroms.

39. (Previously Presented) A dielectric structure for dual-damascene applications as recited in claim 36, wherein a thickness of the low dielectric constant layer of a carbon doped oxide is greater than a thickness of the inorganic dielectric layer of a fluorine doped oxide.

40. (Previously Presented) A dielectric structure for dual-damascene applications as recited in claim 39, wherein the thickness of the inorganic dielectric layer of a fluorine doped oxide is about at least 1,000 Angstroms, and the thickness of the low dielectric constant layer of a carbon doped oxide and the inorganic dielectric layer of a fluorine doped oxide is about 10,000 Angstroms.

41. (Previously Presented) A multi-layer dielectric disposed over a substrate for use in dual-damascene applications, comprising:

a barrier layer disposed over the substrate;

an inorganic dielectric layer of a fluorine doped oxide disposed over the barrier layer, the inorganic dielectric layer having a first thickness; and

a low dielectric constant layer of a carbon doped oxide disposed directly over and in direct contact with the inorganic dielectric layer, the low dielectric constant layer having a second thickness and defining a metallization line layer;

wherein metallization lines are formed in a first portion of the second thickness of the low dielectric constant layer, and a via path is configured to be defined in an entire portion of the first thickness of the inorganic dielectric layer and in at least a portion of the second thickness of the low dielectric constant layer.

42. (Previously presented) The multi-layer dielectric of claim 41, wherein the barrier layer is one of a silicon nitride layer and a silicon carbide layer.

43. (Currently amended) The multi-layer dielectric of claim 41, wherein [[a]] the second thickness of the low dielectric constant layer ~~of a carbon doped oxide~~ is

greater than [[a]] the first thickness of the inorganic dielectric layer ~~of a fluorine doped oxide.~~

44. (Previously presented) The multi-layer dielectric of claim 41, wherein the inorganic dielectric layer has different material properties than the low dielectric constant layer.

45. (Currently amended) The multi-layer dielectric of claim 41, wherein a combined thickness of the first thickness of the inorganic dielectric layer and the second thickness of the low dielectric constant layer is about 10,000 Angstroms.

46. Canceled.

47. (Previously presented) A multi-layer dielectric disposed over a substrate, comprising:

a barrier layer disposed over the substrate; and

an inter-metal dielectric structure, the inter-metal dielectric structure consisting of:

_____ i) _____ an inorganic dielectric layer disposed over the barrier layer, the inorganic dielectric layer having a first thickness; and

_____ ii) _____ a low dielectric constant layer disposed over the inorganic dielectric layer, the low dielectric constant layer having a second thickness and defining a metallization line layer;

wherein metallization lines are formed in a first portion of the second thickness of the low dielectric constant layer, and a via path is configured to be defined in an entire portion of the first thickness of the inorganic dielectric layer and in at least a portion of the second thickness of the low dielectric constant layer.

48. (Previously presented) The multi-layer dielectric of claim 47, wherein the barrier layer is one of a silicon nitride layer and a silicon carbide layer.

49. (Previously presented) The multi-layer dielectric of claim 47, wherein the inorganic dielectric layer is one of an un-doped TEOS oxide and a fluorine doped oxide.

50. (Previously presented) The multi-layer dielectric of claim 47, wherein the low dielectric constant layer is a carbon doped oxide.

51. (Previously presented) The multi-layer dielectric of claim 47, wherein the inorganic dielectric layer has different material properties than the low dielectric constant layer.

52. (Currently amended) The multi-layer dielectric of claim 47, wherein a combined thickness of the first thickness of the inorganic dielectric layer and the second thickness of the low dielectric constant layer is about 10,000 Angstroms.

53. Canceled.

54. (Currently amended) The multi-layer dielectric of claim 47, wherein [[a]] the second thickness of the low dielectric constant layer ~~of a carbon doped oxide~~ is greater than [[a]] the first thickness of the inorganic dielectric layer ~~of a fluorine doped oxide~~.